

Zinc Phosphate Primer

PRODUCT DESCRIPTION A one pack, high build, epoxy ester primer containing zinc phosphate anticorrosive pigment.

INTENDED USES For application to steel on above water areas both internally and externally.
For use at Newbuilding or Maintenance & Repair.

PRODUCT INFORMATION

Colour	CPA226-White
Finish/Sheen	Matt (ISO 2813:1978)
Part B (Curing Agent)	Not applicable
Volume Solids	40% ±2% (ISO 3233:1998)
Mix Ratio	Not applicable
Typical Film Thickness	90 microns dry (225 microns wet)
Theoretical Coverage	4.44 m ² /litre at 90 microns dft, allow appropriate loss factors
Method of Application	Airless Spray, Brush, Conventional Spray, Roller
Flash Point (Typical)	Single Pack 23°C

Drying Information	-5°C	5°C	25°C	35°C
Touch Dry [ISO 9117/3:2010]	16 hrs	8 hrs	6 hrs	4 hrs
Hard Dry [ISO 9117-1:2009]	7 days	5 days	4 days	3 days

Overcoating Data - see limitations	Substrate Temperature							
	-5°C		5°C		25°C		35°C	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Intercare 123	-	-	24 hrs	14 days	6 hrs	14 days	6 hrs	7 days
Interlac 542	48 hrs	28 days	36 hrs	28 days	24 hrs	28 days	24 hrs	28 days
Interlac 665	48 hrs	28 days	36 hrs	28 days	24 hrs	28 days	24 hrs	28 days
Intertherm 891	48 hrs	28 days	36 hrs	28 days	24 hrs	28 days	24 hrs	28 days

REGULATORY DATA **VOC** 472 g/lit as supplied (EPA Method 24)

Note: VOC values are typical and are provided for guidance purposes only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

Zinc Phosphate Primer

SYSTEMS AND COMPATIBILITY

Consult your International Paint representative for the system best suited for the surfaces to be protected.

SURFACE PREPARATIONS

Use in accordance with the standard Worldwide Marine Specifications.

All surfaces to be coated should be clean, dry and free from contamination.

High pressure fresh water wash or fresh water wash, as appropriate, and remove all oil or grease, soluble contaminants and other foreign matter in accordance with SSPC-SP1 solvent cleaning.

NEWBUILDING

Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

Where necessary, remove weld spatter and smooth weld seams and sharp edges.

Clean welds and damaged shop primer by power tooling to Pt2 (JSRA SPSS:1984).

Ensure that the area is clean and dry prior to application of Interprime 226.

MAJOR REFURBISHMENT

Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

Abrasive blast clean to Sa2½ (ISO 8501-1:2007). If oxidation has occurred between blasting and application of Interprime 226, the surface should be reblasted to the specified visual standard.

Ensure that the area is clean and dry prior to application of Interprime 226.

Consult your International Paint representative for specific recommendations.

NOTE

For use in Marine situations in North America, the following surface preparation standards can be used:

SSPC-SP10 in place of Sa2½ (ISO 8501-1:2007)

SSPC-SP2 in place of St2 (ISO 8501-1:2007)

Zinc Phosphate Primer

APPLICATION

Mixing	This material is a one pack coating and should always be mixed thoroughly with a power agitator before application.
Thinner	Not Recommended. Use International GTA004 only in exceptional circumstances (max 5% by volume). DO NOT thin more than allowed by local environmental legislation.
Airless Spray	Recommended Tip Range 0.46-0.53 mm (18-21 thou) Total output fluid pressure at spray tip not less than 176 - 211 kg/cm ² (2500 - 3000 p.s.i.)
Conventional Spray	Use suitable proprietary equipment. Thinning may be required.
Brush	Suitable. Multiple coats may be required to achieve specified film thickness.
Roller	Suitable. Multiple coats may be required to achieve specified film thickness.
Cleaner	International GTA004
Work Stoppages and Cleanup	Thoroughly flush all equipment with International GTA004. All unused material should be stored in tightly closed containers. Partially filled containers may show surface skinning and/or a viscosity increase of the material after storage. Material should be filtered prior to use.
Welding	In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety in Welding and Cutting."

SAFETY

All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.

Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.

EMERGENCY CONTACT NUMBERS:

USA/Canada - Medical Advisory Number 1-800-854-6813

Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191

R.O.W. - Contact Regional Office

Zinc Phosphate Primer

LIMITATIONS

This product should not be used under continuously immersed conditions or for cathodically protected boottops.

Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Paint representative for specific recommendations.

Apply in good weather. Temperature of the surface to be coated must be at least 3°C above the dew point. For optimum application properties bring the material to 21-27°C, unless specifically instructed otherwise, prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage in accordance with information given in the STORAGE Section of this data sheet. Technical and application data herein is for the purpose of establishing a general guideline of the coating application procedures. Test performance results were obtained in a controlled laboratory environment and International Paint makes no claim that the exhibited published test results, or any other tests, accurately represent results found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance and use of the coating.

UNIT SIZE	Unit Size	Part A	
		Vol	Pack
	20 lt	20 lt	20 lt
For availability of other unit sizes consult International Paint			
UNIT SHIPPING WEIGHT (TYPICAL)	Unit Size	Unit Weight	
	20 lt	30.51 Kg	
STORAGE	Shelf Life	12 months minimum at 25°C. Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.	

WORLDWIDE AVAILABILITY Consult International Paint.

IMPORTANT NOTE

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

© AkzoNobel, 2018

www.international-marine.com