

Copper Free, Low Friction, Self Polishing Copolymer A/F

PRODUCT DESCRIPTION A high solids, high performance, TBT free, copper free, low friction, self polishing Copolymer (SPC) antifouling with patented copper acrylate technology. Particularly suitable for fouling protection under static conditions and in service trading.

INTENDED USES Developed especially to meet the severe fouling challenges of vessels during Newbuilding fitting out and also in service trading.
Designed for use at newbuilding fitting out and in service trading under severe fouling conditions. Suitable as part of an overall scheme with all Intersmooth and Intercept deep sea products, depending on activity profile and intended service life.
For use at Newbuilding and Maintenance & Repair.

PRODUCT INFORMATION

Colour	BEA974-Brown, BEA977-Red and a limited range of colours
Finish/Sheen	Sheen
Part B (Curing Agent)	Not applicable
Volume Solids	57% ±2% (ISO 3233:1998)
Typical Film Thickness	Range: 75 - 190 microns dry (132 - 334 microns wet) may be specified depending on end use.
Theoretical Coverage	Range: 7.6 - 3.0 m ² /litre at 75 - 190 microns dft, allow appropriate loss factors
Method of Application	Airless Spray, Brush, Roller
Flash Point (Typical)	Single Pack 26°C

Drying Information	-5°C	5°C	25°C	35°C				
Touch Dry [ISO 9117/3:2010]	120 mins	60 mins	40 mins	30 mins				
Before Flooding	30 hrs	18 hrs	12 hrs	10 hrs				
Overcoating Data - see limitations	Substrate Temperature							
	-5°C		5°C		25°C		35°C	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Interflex 8700 SPC	12 hrs	6 mths	6 hrs	6 mths	4 hrs	6 mths	3 hrs	6 mths

REGULATORY DATA **VOC** 383 g/lit as supplied (EPA Method 24)

Note: VOC values are typical and are provided for guidance purposes only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

This product does not contain organotin compounds acting as biocides and as such is in compliance with the International Convention on the Control of Harmful Anti-fouling Systems on ships as adopted by IMO in October 2001 (IMO document AFS/CONF/26).

Copper Free, Low Friction, Self Polishing Copolymer A/F

CERTIFICATION

When used as part of an approved scheme, this product has the following certification:

Product recognised by the following classification societies as compliant with the International Convention on the Control of Harmful Anti-fouling Systems on Ships, 2001 (AFS 2001):

- Bureau Veritas
- DNV GL
- Korean Register of Shipping
- Lloyds Register

Consult your International Paint representative for details.

SYSTEMS AND COMPATIBILITY

Consult your International Paint representative for the system best suited for the surfaces to be protected.

SURFACE PREPARATIONS

Use in accordance with the standard Worldwide Marine Specifications. All surfaces to be coated must be clean, dry and free from contamination. High pressure fresh water wash or fresh water wash, as appropriate, and remove all oil, grease, soluble contaminants and other foreign matter in accordance with SSPC-SP1 : solvent cleaning.

NEWBUILDING

Interflex 8700 SPC should always be applied over a recommended anti-corrosive coating scheme. The primer surface should be dry and free from all contamination, and Interflex 8700 SPC must be applied within the overcoating intervals specified (consult the relevant product data sheet.) Areas of breakdown, damage etc., should be prepared to the specified standard (e.g. Sa2½ (ISO 8501-1:2007) and primed prior to the application of Interflex 8700 SPC

Application of Interflex 8700 SPC over International Paint Intersmooth SPC or competitors antifouling;

Consult your International Paint representative for specific recommendations.

Copper Free, Low Friction, Self Polishing Copolymer A/F

APPLICATION

Mixing	This material is a one pack coating and should always be mixed thoroughly with a power agitator before application.
Thinner	Not Recommended. Use International GTA007 only in exceptional circumstances (max 5% by volume). DO NOT thin more than allowed by local environmental legislation.
Airless Spray	Recommended Tip Range 0.63-0.79 mm (25-31 thou) Total output fluid pressure at spray tip not less than 211 kg/cm ² (3000 p.s.i.)
Conventional Spray	Application by conventional spray is not recommended.
Brush	Application by brush is recommended for small areas only. Multiple coats may be required to achieve specified film thickness.
Roller	Application by roller is recommended for small areas only. Multiple coats may be required to achieve specified film thickness.
Cleaner	International GTA007
Work Stoppages and Cleanup	Thoroughly flush all equipment with GTA007. All unused material should be stored in tightly closed containers. Partially filled containers may show a viscosity increase of the material after storage. Material should be filtered prior to use.
Welding	In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety in Welding and Cutting."

SAFETY

All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.

Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.

EMERGENCY CONTACT NUMBERS:

USA/Canada - Medical Advisory Number 1-800-854-6813

Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191

South Korea - Contact Regional Office (82) 55-632-6286 / (82) 55-586-2310

R.O.W. - Contact Regional Office

Copper Free, Low Friction, Self Polishing Copolymer A/F

LIMITATIONS

Following immersion, this product will brighten in colour.

Apply in good weather. Temperature of the surface to be coated must be at least 3°C above the dew point. For optimum application properties bring the material to 21-27°C, unless specifically instructed otherwise, prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage in accordance with information given in the STORAGE Section of this data sheet. Technical and application data herein is for the purpose of establishing a general guideline of the coating application procedures. Test performance results were obtained in a controlled laboratory environment and International Paint makes no claim that the exhibited published test results, or any other tests, accurately represent results found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance and use of the coating.

UNIT SIZE	Unit Size	Part A	
		Vol	Pack
	15 lt	15 lt	15 lt

For availability of other unit sizes consult International Paint

UNIT SHIPPING WEIGHT (TYPICAL)	Unit Size	Unit Weight
	15 lt	24.2 Kg

STORAGE	Shelf Life	12 months at 25°C. Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.
---------	------------	---

WORLDWIDE AVAILABILITY Consult International Paint.

IMPORTANT NOTE

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

© AkzoNobel, 2018

www.international-marine.com