

Alkyd Primer

PRODUCT DESCRIPTION A fast drying, modified alkyd primer, with good substrate tolerance. Can be overcoated with alkyd, polyurethane, acrylic, and other thermoplastic finishes. Simplifies painting for the crew and minimizes costs of on board maintenance by reducing paint stock and wastage. Low VOC.

INTENDED USES An anticorrosive primer for above water areas, including holds and internals. For use at Maintenance & Repair or On Board Maintenance.

PRODUCT INFORMATION

Colour	CPA098V-Grey, CPA099V-Red
Finish/Sheen	Not applicable
Part B (Curing Agent)	One pack
Volume Solids	59% ±2% (ASTM D2697-86)
Mix Ratio	One pack
Typical Film Thickness	3.0 mils dry (5.1 mils wet) 3.0-3.5 mils (76 - 89 microns) dry practical range equivalent 5.1-5.9 mils (129 - 151 microns) wet
Theoretical Coverage	7.76 m ² /lt at 76 microns dft, allow appropriate loss factors
Method of Application	Airless Spray, Brush, Conventional Spray, Roller
Flash Point (Typical)	Single Pack 26°C (Setaflash) (ASTM D-3278)

Drying Information	5°C	10°C	25°C	35°C
Touch Dry [ASTM D1640 7.5.1]	4 hrs	3.5 hrs	2 hrs	60 mins
Hard Dry [ASTM D1640 7.7]	24 hrs	17 hrs	6 hrs	4 hrs

Overcoated By	Overcoating Data - see limitations							
	Substrate Temperature							
	5°C		10°C		25°C		35°C	
	Min	Max	Min	Max	Min	Max	Min	Max
Interfine 599	9 hrs	24 hrs	7.5 hrs	20 hrs	4 hrs	12 hrs	2 hrs	6 hrs
Interlac 665	6 hrs	48 hrs	6 hrs	45 hrs	4 hrs	36 hrs	2 hrs	24 hrs
Interprime 298	6 hrs	ext	5.5 hrs	ext	4 hrs	ext	2 hrs	ext
Intersheen 579	24 hrs	48 hrs	20 hrs	45 hrs	12 hrs	36 hrs	8 hrs	24 hrs

REGULATORY DATA **VOC** 340 g/lt (2.84 lb/US Gal) as supplied (EPA Method 24)

Note: VOC values are typical and are provided for guidance purposes only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

Alkyd Primer

SYSTEMS AND COMPATIBILITY

Consult your International Paint representative for the system best suited for the surfaces to be protected.

SURFACE PREPARATIONS

Paint only clean, dry surfaces. Remove all grease, oil, soluble contaminants and other foreign matter by "solvent cleaning" (SSPC-SP1).

Steel:

For optimum performance "Near White Blast Cleaning" (SSPC-SP10) is recommended.

"Commercial Blast Cleaning" (SSPC-SP6) is acceptable in many areas. Consult your International Paint representative for specific recommendations.

Previously Painted Surfaces:

Remove all mill scale, loose rust, loose paint and other foreign matter by "Hand or Power Tool Cleaning" (SSPC-SP2 or SP3, respectively).

Apply one or more spot coats of Interprime 298, as specified.

Alkyd Primer

APPLICATION

Mixing	This material is a one pack coating. Always mix thoroughly with a power agitator before application.
Thinner	GTA007. Not normally required. DO NOT THIN BEYOND YOUR STATE'S COMPLIANCY. Material is supplied at spray viscosity and normally does not need thinning. If thinning is necessary, thin up to a maximum of 4 ounces (118 ml) per gallon (3.79 lt) with International GTA007 Thinner.
Airless Spray	Minimum 28:1 ratio pump; 0.018" - 0.021" (475-533 microns) orifice tip; 3/8" ID high pressure material hose; 60 mesh tip filter
Conventional Spray	DeVilbiss MBC-510 gun E tip and 704 air cap; 3/8" (9.5 mm) ID material hose; double regulated pressure tank with oil and moisture separator.
Brush	Use appropriate size China bristle brush.
Roller	Use All Purpose Roller cover with 3/8" (9.5 mm) smooth to medium nap. Prewash roller cover to remove loose fibres prior to use.
Cleaner	International GTA007
Work Stoppages and Cleanup	Clean all equipment immediately after use with International GTA007. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency will depend upon factors such as amount sprayed, temperature and elapsed time including work stoppages. Monitor material condition. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.
Welding	In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety in Welding and Cutting."

SAFETY

All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.

Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.

EMERGENCY CONTACT NUMBERS:

USA/Canada - Medical Advisory Number 1-800-854-6813

Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191

R.O.W. - Contact Regional Office

Alkyd Primer

LIMITATIONS

Apply in good weather when air and surface temperatures are above 2°C. Surface temperatures must be at least 3°C above dew point. For optimum application properties, bring material to 21-27°C prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage between 4-38°C.

When topcoating with strong solvent coatings, such as epoxies or polyurethanes the recoat intervals will vary depending upon the specific temperature and humidity conditions. In accordance with good painting practice, a small test patch should be made prior to application over a large area. Consult your International Paint representative for specific recommendations.

Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Paint representative for specific recommendations. Technical and application data herein is for the purpose of establishing a general guideline of the coating and proper coating application guidelines. Test performance results were obtained in a controlled laboratory environment and International Paint makes no claim that the exhibited published test results, or any other tests, accurately represent results actually found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance and use of the coating. In the overcoating data section 'ext' = extended overcoating period. Please refer to our Marine Painting Guide - Definitions and Abbreviations available on our website.

UNIT SIZE	Unit Size	Vol	Pack
	1 US gal	1 US gal	1 US gal
5 US gal	5 US gal	5 US gal	5 US gal

For availability of other unit sizes consult International Paint

UNIT SHIPPING WEIGHT (TYPICAL)	Unit Size	Unit Weight
	1 US gal	12.6 lb
5 US gal	62.5 lb	

STORAGE	Shelf Life	24 months minimum from date of manufacture when maintained in protected storage at 4-38°C
		Subject to reinspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.

WORLDWIDE AVAILABILITY Consult International Paint.

IMPORTANT NOTE

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

© AkzoNobel, 2015

www.international-marine.com