

Epoxy Universal Primer

PRODUCT DESCRIPTION A light coloured, epoxy universal primer.

INTENDED USES For use as an anticorrosive universal primer in ballast tanks, outer hull, cofferdams, void spaces, decks, cargo holds and crude oil tanks.
Suitable for use with controlled cathodic protection.
For use at Newbuilding or Maintenance & Repair.

PRODUCT INFORMATION

Colour	KUA602-Grey, KUA606-Red
Finish/Sheen	Not applicable
Part B (Curing Agent)	KUA603
Volume Solids	68% ±2% (ISO 3233:1998)
Mix Ratio	4 volume(s) Part A to 1 volume(s) Part B
Typical Film Thickness	160 microns dry (235 microns wet)
Theoretical Coverage	4.25 m ² /litre at 160 microns dft, allow appropriate loss factors
Method of Application	Airless Spray, Brush, Roller
Flash Point (Typical)	Part A 26°C; Part B 33°C; Mixed 27°C

Drying Information	5°C	10°C	25°C	35°C
Touch Dry [ISO 9117/3:2010]	26 hrs	22 hrs	9 hrs	3 hrs
Hard Dry [ISO 9117-1:2009]	40 hrs	30 hrs	12 hrs	5 hrs
Pot Life	6 hrs	5 hrs	4 hrs	2 hrs

Overcoating Data - see limitations	Substrate Temperature							
	5°C		10°C		25°C		35°C	
	Min	Max	Min	Max	Min	Max	Min	Max
Overcoated By								
Intergard 263	24 hrs	4 mths	16 hrs	4 mths	6 hrs	4 mths	4 hrs	3 mths
Intergard 269	40 hrs	6 mths	30 hrs	6 mths	12 hrs	6 mths	6 hrs	5 mths
Intergard 410	40 hrs	4 mths	30 hrs	4 mths	12 hrs	4 mths	6 hrs	3 mths
Intergard 5600 Immersed Areas	40 hrs	28 days	30 hrs	28 days	12 hrs	28 days	6 hrs	21 days
Intergard 5600 Non Immersed Areas	40 hrs	4 mths	30 hrs	4 mths	12 hrs	4 mths	6 hrs	3 mths
Intergard 740	24 hrs	28 days	18 hrs	28 days	6 hrs	28 days	4 hrs	21 days
Interthane 990	40 hrs	5 days	30 hrs	5 days	12 hrs	5 days	6 hrs	3 days

REGULATORY DATA **VOC** 304 g/lit as supplied (EPA Method 24)
305 g/lit Chinese National Standard GB23985

Note: VOC values are typical and are provided for guidance purposes only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

Epoxy Universal Primer

CERTIFICATION

When used as part of an approved scheme, this material has the following certification:

- Food Contact - Carriage of Grain (NOHH)
- Fire Resistance - Marine Equipment Directive compliant
- Fire Resistance - Surface Spread of Flame (Exova Warringtonfire)
- Fire Resistance - Smoke & Toxicity (Exova Warringtonfire)

Consult your International Paint representative for details.

SYSTEMS AND COMPATIBILITY

Consult your International Paint representative for the system best suited for the surfaces to be protected.

SURFACE PREPARATIONS

Use in accordance with the standard Worldwide Marine Specifications.

All surfaces to be coated must be clean, dry and free from contamination.

High pressure fresh water wash or fresh water wash, as appropriate, and remove all oil or grease, soluble contaminants and other foreign matter in accordance with SSPC-SP1 solvent cleaning.

Intergard 5600 can be applied over Intergard 269, when used as a holding primer to protect the blast. The primer surface should be dry and free from all contamination and Intergard 5600 must be applied within the overcoating interval specified (consult the Intergard 269 product data sheet).

NEWBUILDING

Where necessary, remove weld spatter and smooth weld seams and sharp edges.

Weld seams and areas of shop primer damage or breakdown should be blast cleaned to Sa2½ (ISO 8501-1:2007) or power tooled to Pt3 (JSRA SPSS:1984).

Intact, approved, shop primers must be clean, dry and free from soluble salts and any other surface contaminants.

Unapproved shop primers will require complete removal by blast cleaning to Sa2½ (ISO 8501-1:2007). In some cases sweep blasting to a defined International Paint standard (eg AS2 or AS3) may be acceptable. Consult your International Paint representative for specific recommendations.

MAJOR REFURBISHMENT

Abrasive blast clean to Sa2½ (ISO 8501-1:2007).

Or

International Paint Hydroblasting Standard HB2 where flash rust is no worse than HB2M. Hydroblasting is only recommended for underwater hull, above water or topside areas.

Or

International Paint Slurry Blasting Standard SB2 where flash rust is no worse than SB2M. Slurry blasting is only recommended for underwater hull, above water and topside areas.

REPAIR

Consult International Paint.

For blasted areas, the primer should be applied before oxidation occurs. If oxidation does occur, the entire oxidised area should be reblasted to the specified standard above.

OBM

For tank coating projects, consult International Paint for the detailed tank coating procedures that should be followed.

Consult your International Paint representative for specific recommendations and procedures.

Epoxy Universal Primer

APPLICATION

Mixing	Material is supplied in 2 containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified. (1) Agitate Base (Part A) with a power agitator. (2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.
Thinner	International GTA220. Thinning is not normally required. Consult the local representative for advice during application in extreme conditions. Do not thin more than allowed by local environmental legislation.
Airless Spray	Recommended Tip Range 0.53-0.66 mm (21-26 thou) Total output fluid pressure at spray tip not less than 176 kg/cm ² (2500 p.s.i.)
Brush	Application by brush is recommended for small areas only. Multiple coats may be required to achieve specified film thickness.
Roller	Application by roller is recommended for small areas only. Multiple coats may be required to achieve specified film thickness.
Cleaner	International GTA415/GTA822
Work Stoppages and Cleanup	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA415/GTA822. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units. Clean all equipment immediately after use with International GTA415/GTA822. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays. Do not exceed pot life limitations. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.
Welding	In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety in Welding and Cutting."

SAFETY

All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.

Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.

EMERGENCY CONTACT NUMBERS:

USA/Canada - Medical Advisory Number 1-800-854-6813

Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191

China - Contact (86) 532 83889090

R.O.W. - Contact Regional Office

Epoxy Universal Primer

LIMITATIONS

This product will not cure adequately below 5°C.
 For maximum performance, the curing temperature should be above 10°C.
 Drying times and overcoating intervals may alter due to on-site factors such as tank configuration or ventilation rates etc.
 Intergard 5600 must not be used in mixed schemes with Intergard 5620.

Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Paint representative for specific recommendations. Apply in good weather. Temperature of the surface to be coated must be at least 3°C above the dew point. For optimum application properties bring the material to 21-27°C, unless specifically instructed otherwise, prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage in accordance with information given in the STORAGE Section of this data sheet. Technical and application data herein is for the purpose of establishing a general guideline of the coating application procedures. Test performance results were obtained in a controlled laboratory environment and International Paint makes no claim that the exhibited published test results, or any other tests, accurately represent results found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance and use of the coating.

Under certain climatic conditions, particularly at low temperature and high humidity, amine bloom can occur on the coating surface during drying. In order to prevent this, an induction period of 30 minutes is recommended between mixing and paint application at temperatures below 25°C.

UNIT SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	20 lt	16 lt	20 lt	4 lt	5 lt
<i>For availability of other unit sizes consult International Paint</i>					
UNIT SHIPPING WEIGHT (TYPICAL)	Unit Size	Unit Weight			
	20 lt	28.84 Kg			
STORAGE	Shelf Life	12 months at 25°C. Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.			

WORLDWIDE AVAILABILITY Consult International Paint.

IMPORTANT NOTE

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

© AkzoNobel, 2019

www.international-marine.com