

## Water Based Inorganic Shop Primer

**PRODUCT DESCRIPTION** A two pack, heat resistant, water based shop (pre-construction) primer providing corrosion protection (even after heating up to 800°C) and resistance to damage caused by welding, gas cutting and fairing. Suitable for fast welding processes and offers control of secondary surface preparation.

**INTENDED USES** As a shop (pre-construction) primer for the short term protection of steel during fabrication and assembly. Suitable for use with controlled cathodic protection. For use at Newbuilding.

**PRODUCT INFORMATION**

<b>Colour</b>	ZER020/ZER021-Grey (ZER022-Red available upon request)
<b>Finish/Sheen</b>	Matt
<b>Part B (Curing Agent)</b>	ZER021 (Powder)
<b>Volume Solids</b>	36% ±2% (ISO 3233:1998)
<b>Mix Ratio</b>	5.34 volume(s) Part A to 1 volume(s) Part B
<b>Typical Film Thickness</b>	15 microns dry (42 microns wet)
<b>Theoretical Coverage</b>	24 m <sup>2</sup> /litre at 15 microns dft, allow appropriate loss factors
<b>Method of Application</b>	Airless Spray, Brush, Conventional Spray, Roller
<b>Flash Point (Typical)</b>	Not applicable

<b>Drying Information</b>	5°C	10°C	25°C	35°C
Hard Dry [ISO 9117-1:2009]			4 mins	2 mins
Pot Life			16 hrs	12 hrs

**Note** (a) It is recommended to pre-heat the steel to 30-35°C prior to applying Interplate Zero Eco. After application, it is also recommended to post-cure Interplate Zero Eco to 30-35°C for 15 seconds minimum.  
 (b) At higher than specified film thickness or under application conditions of high humidity, a minimum steel temperature of 40°C is recommended.

<b>Overcoating Data - see limitations</b>	<b>Substrate Temperature</b>							
	5°C		10°C		25°C		35°C	
<b>Overcoated By</b>	Min	Max	Min	Max	Min	Max	Min	Max

**Note** Consult International Paint, minimum of 7 days for appropriate primers.

**REGULATORY DATA**

<b>VOC</b>	0 g/lit calculated 0 g/kg of liquid paint as supplied. EU Solvent Emissions Directive (Council Directive 1999/13/EC)
------------	-------------------------------------------------------------------------------------------------------------------------

**Note:** VOC values are typical and are provided for guidance purposes only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

## Water Based Inorganic Shop Primer

### CERTIFICATION

When used as part of an approved scheme, this material has the following certification:

- Weld Quality - Approval of Prefabrication Primers (LR)
- Weld Quality - Shop Primers for Corrosion Protection of Steel Plates and Structures (DNV)
- Weld Quality - Shop Primers for Welded Steel Structures (BV)

Consult your local representative for details.

---

### SYSTEMS AND COMPATIBILITY

Consult your local representative for the system best suited for the surfaces to be protected.

---

### SURFACE PREPARATIONS

Use in accordance with the standard Worldwide Marine Specifications.

All surfaces to be coated should be clean, dry and free from contamination.

High pressure fresh water wash or fresh water wash, as appropriate, and remove all oil or grease, soluble contaminants and other foreign matter in accordance with SSPC-SP1 solvent cleaning.

#### NEWBUILDING

Shop primers should be applied using automatic blasting/spraying equipment.

Blast to a minimum of Sa2½ (ISO 8501-1:2007).

Consult your local representative for specific recommended abrasives and surface profiles.

Apply Interplate Zero Eco before oxidation occurs. If oxidation does occur the entire oxidised area should be reblasted to the standard specified above.

Ensure that the area is clean and dry prior to application of Interplate Zero Eco.

Consult your local representative for specific recommendations.

#### NOTE

**For use in Marine situations in North America, the following surface preparation standards can be used: SSPC-SP10 in place of Sa2½ (ISO 8501-1:2007)**

## Water Based Inorganic Shop Primer

### APPLICATION

<b>Mixing</b>	Material is supplied in 2 separate containers as a unit. Always mix a complete unit in the proportions supplied. Agitate the binder (Part A) with a power agitator then slowly add the powder (Part B) whilst continuing agitating. Where product is supplied as a 17.8 litre unit it will be necessary to transfer Part A to a separate suitable container prior to adding Part B. Allow to mix for at least 5 minutes, sieve through a 30-60 mesh screen before use. Continue stirring during use. <b>Always add Powder to Binder.</b>
<b>Thinner</b>	Not recommended. Consult your International Paint representative.
<b>Airless Spray</b>	Recommended Tip Range 0.38-0.58 mm (15-23 thou) Total output fluid pressure at spray tip not less than 60 - 100 kg/cm <sup>2</sup> (850 - 1420 p.s.i.)
<b>Conventional Spray</b>	Recommended
<b>Brush</b>	Application by brush is recommended for small areas only. Multiple coats may be required to achieve specified film thickness.
<b>Roller</b>	Application by roller is recommended for small areas only. Multiple coats may be required to achieve specified film thickness.
<b>Cleaner</b>	Potable Water.
<b>Work Stoppages and Cleanup</b>	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with potable water. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units, to ensure that the potlife has not been exceeded. Clean all equipment immediately after use with water. Spray equipment requires flushing with water. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency will depend upon factors such as amount sprayed, temperature and elapsed time including work stoppages. Monitor material condition. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.
<b>Welding</b>	<b>Hot Work</b> In the event welding or flame cutting or fairing is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety in Welding and Cutting."

### SAFETY

**All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.**

Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.

#### EMERGENCY CONTACT NUMBERS:

USA/Canada - Medical Advisory Number 1-800-854-6813

Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191

R.O.W. - Contact Regional Office

## Water Based Inorganic Shop Primer

### LIMITATIONS

Drying times will depend on the substrate temperature and ventilation conditions.  
 If the relative humidity is below 50%, cure will be retarded.  
 Interplate Zero Eco is not recommended for manual spray application.  
 At higher dry film thickness, fabrication properties (welding and cutting) may be affected.  
 Shop primers are not recommended for use as touch-up primers after fabrication.

Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Paint representative for specific recommendations. The temperature of the surface to be coated must be at least 3°C above the dew point. For optimum application properties bring the material to 21-27°C, unless specifically instructed otherwise, prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage in accordance with the information given in the STORAGE section of this data sheet.

UNIT SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	17.8 lt	15 lt	15 lt	2.8 lt	20 lt
Part A is supplied in a polyethylene container Part B is supplied in a steel container For availability of other unit sizes consult International Paint					

UNIT SHIPPING WEIGHT (TYPICAL)	Unit Size	Unit Weight
	17.8 lt	31.01 Kg

STORAGE	Shelf Life	Cool dry conditions Part A must be kept above 5°C
		Part A - 6 months maximum from date of manufacture at temperatures up to 25°C. Part B - 18 months minimum from date of manufacture at temperatures up to 25°C. Subject to reinspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.

**WORLDWIDE AVAILABILITY** Consult International Paint.

### IMPORTANT NOTE

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.*

*This Technical Data Sheet is available on our website at [www.international-marine.com](http://www.international-marine.com) or [www.international-pc.com](http://www.international-pc.com), and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.*

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

© AkzoNobel, 2017

[www.international-marine.com](http://www.international-marine.com)