# Interline<sub>®</sub> 975P

#### Solvent-free tank lining



#### **Product Description**

Interline® 975P is a two component, solvent-free, heavy duty epoxy lining. It provides corrosion protection for the internals of potable water tanks and liquid mud tanks.

With a 100% volume solids, zero VOC formulation, Interline 975P is designed to reduce solvent emissions and eliminate the risk of solvent retention, which can influence water quality. The absence of Benzyl Alcohol further minimizes the occurrence of taste or smell in potable water tanks during storage.

Suitable for application as a one-coat or two-coat system using standard airless spray equipment.

Interline 975P can be applied at Newbuilding, Maintenance and Repair, and for Onboard Maintenance.

### **Key features**

Solvent free, high build, amine cured epoxy tank lining

Certified to NSF/ANSI 61 standard for the storage of potable water for tanks 50 gallons and greater

100% solids, zero VOC formulation which eliminates solvent emission, explosion risk and fire hazard

Benzyl Alcohol free, further reducing the risk of taste and smell in potable water tanks

Suitable for application as a one-coat or two-coat system, using standard airless spray equipment

Recoatable up to 28 days for improved scheduling of contracts

Suitable for use in liquid mud tanks

### **Product Information**

Color	White 100% 12 - 24 mils (300 - 600 μm) dry			
Volume solids Typical film thickness Temperature				
	50°F (10°C)	15 hours	36 hours	28 days
59°F (15°C)	12 hours	24 hours	28 days	
77°F (25°C)	7 hours	16 hours	21 days	
104°F (40°C)	3 hours	6 hours	14 days	

#### voc

0.0 lb/gal (0 g/l) - Calculated

For each of our products the relevant Product Data Sheet, Material Safety Data Sheet and package labelling comprise an integral information system about the product in question. Copies of our Product Data Sheets and Material Safety Data Sheets are available on request or from our website.

Unless otherwise agreed in writing, all products supplied and technical advice or recommendations given are subject to the Conditions of Sale of our supplying company and the provisions of the relevant product data sheet.

## To find out more visit: www.international-marine.com

S, International and all products mentioned in this publication are trademarks of or are licensed to AkzoNobel © AkzoNobel, 2017 Global Marine Coatings Headquarters International Paint Singapore Pte Ltd, 21, Tuas South Street 3, Singapore 638023. Call: +65 6594 8800 Fax: +65 6594 8897

