

IMO Resolution MSC.215 (82) compliant Zinc Silicate Shop Primer

PRODUCT DESCRIPTION A two pack, zinc ethyl silicate shop (pre-construction) primer.

INTENDED USES As a shop (pre-construction) primer for the protection of steel during fabrication and assembly. Suitable for use with controlled cathodic protection. For use at Newbuilding.

PRODUCT INFORMATION

Colour	NQA311-Grey
System Film Thickness	1 coat at 15 microns dry (54 microns wet) per coat
Finish/Sheen	Matt
Part B (Curing Agent)	NQA317
Volume Solids	28% ±2% (ISO 3233:1998)
Mix Ratio	1 volume(s) Part A to 1 volume(s) Part B
Specific Gravity	Paste (Part A) 1.86-1.92 Binder (Part B) 0.86-0.90 Mixed Paint 1.355-1.405
Theoretical Coverage	18.67 m ² /litre at 15 microns dft, allow appropriate loss factors
Method of Application	Airless Spray, Brush, Conventional Spray, Roller
Flash Point (Typical)	Part A 13°C; Part B 6°C; Mixed 6°C

Drying Information	5°C		10°C		25°C		35°C	
Hard Dry [ISO 9117-1:2009]					5 mins		4 mins	
Pot Life	8 hrs		7 hrs		6 hrs		5 hrs	
Overcoating Data - see limitations	Substrate Temperature							
	5°C		10°C		25°C		35°C	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max

Note Consult International Paint, minimum of 24 hours for appropriate primers.

REGULATORY DATA

VOC	609 g/lit calculated 411 g/kg of liquid paint as supplied. EU Solvent Emissions Directive (Council Directive 1999/13/EC)
------------	---

Note: VOC values are typical and are provided for guidance purposes only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

IMO Resolution MSC.215 (82) compliant Zinc Silicate Shop Primer

CERTIFICATION

When used as part of an approved scheme, this material has the following certification:

- Weld Quality - Approval of Prefabrication Primers (LR)
- Weld Quality - Shop Primers for Corrosion Protection of Steel Plates and Structures (DNV)
- Weld Quality - Weldable Prefabrication Shop Primer (ABS)
- Weld Quality - Approved for Overweldable Shop Primers (GL)
- Weld Quality - Welding Shop Primer for Steel Structure (KR)

- IMO PSPC Resolution MSC.215 (82) - Lloyds Register (LR)
- IMO PSPC Resolution MSC.215 (82) - Det Norske Veritas (DNV)
- IMO PSPC Resolution MSC.215 (82) - Registro Italiano Navale (RINA)
- IMO PSPC Resolution MSC.215 (82) - Germanischer Lloyd (GL)
- IMO PSPC Resolution MSC.215 (82) - American Bureau of Shipping (ABS)
- IMO PSPC Resolution MSC.215 (82) - China Classification Society (CCS)

Consult your International Paint representative for details.

SURFACE PREPARATIONS

Use in accordance with the standard Worldwide Marine Specifications.
All surfaces to be coated should be clean, dry and free from contamination.

NEWBUILDING

Shop primers should be applied using automatic blasting/spraying equipment.
Blast to a minimum of Sa2½ (ISO 8501-1:2007) or St2 for insulation part inside. Steel grit or a mixture of steel grit of particle size 0.6-1.0mm (24-39 mils) and steel shot of particles size 0.6-1.4mm (24-55 mils) are normally used to give a predominantly angular profile.
Apply Interplate 317 before oxidation occurs. If oxidation does occur the entire oxidised area should be reblasted to the standard specified above.

Cleanliness

All surfaces to be coated must be clean, dry and free from contamination.

Residual dust levels prior to paint application must not exceed rating "1" for dust size classes "3", "4" or "5" (ISO 8502-3:1993).

Residual soluble salt levels prior to coating application must not exceed 50mg/m² as extracted and measured in accordance with ISO 8502-6 (1995) and ISO 8502-9 (1998) respectively.

Surface profile

The surface profile must lie in the range 30-75 microns (ISO 8503-1/2:1988).

NOTE

**For use in Marine situations in North America, the following surface preparation standards can be used:
SSPC-SP10 in place of Sa2½ (ISO 8501-1:2007)**

IMO Resolution MSC.215 (82) compliant Zinc Silicate Shop Primer

APPLICATION

Mixing	Interplate 317 is supplied in 2 parts, a liquid Binder base component (Part A) and a Powder component (Part B). The Powder (Part B) should be slowly added to the liquid Binder (Part A) whilst stirring with a mechanical agitator. DO NOT ADD LIQUID TO POWDER. Material should be filtered prior to application and should be constantly agitated in the pot during spraying. Once the unit has been mixed it should be used within the working pot life specified.
Thinner	Not recommended. Use International GTA136 only in exceptional circumstances (max 5% by volume). DO NOT thin more than allowed by local environmental legislation.
Airless Spray	Recommended Tip Range 0.43-0.53 mm (17-21 thou) Total output fluid pressure at spray tip not less than 70 - 141 kg/cm ² (1000 - 2010 p.s.i.)
Conventional Spray	Use suitable proprietary equipment. Thinning may be required.
Brush	Application by brush is recommended for small areas only. Multiple coats may be required to achieve specified film thickness.
Roller	Application by roller is recommended for small areas only. Multiple coats may be required to achieve specified film thickness. Brush and roller are not suitable for application of full coats. Airless spray should be used for the latter.
Cleaner	International GTA803
Work Stoppages and Cleanup	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA803. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units. Clean all equipment immediately after use with International GTA803. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays. Do not exceed pot life limitations. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.
Welding	In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety in Welding and Cutting."

SAFETY

All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.

Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.

EMERGENCY CONTACT NUMBERS:

USA/Canada - Medical Advisory Number 1-800-854-6813

Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191

China – Contact (86) 532 83889090

R.O.W. - Contact Regional Office

IMO Resolution MSC.215 (82) compliant Zinc Silicate Shop Primer

LIMITATIONS

Drying times will depend on the substrate temperature and ventilation conditions. If the relative humidity is below 50%, cure will be retarded. Interplate 317 is not recommended for manual spray application. Shop primers are not recommended for use as touch-up primers after fabrication.

Film Thickness

Minimum Film Thickness

Film thicknesses below the specified 15 microns may result in premature breakdown of the shop primer and substrate corrosion, necessitating additional secondary surface preparation.

Maximum Film Thickness

Film thicknesses above the specified 15 microns may adversely affect welding and cutting properties and may affect the performance of subsequently applied coating systems. Thicknesses above 25 microns should be avoided.

Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Paint representative for specific recommendations. The temperature of the surface to be coated must be at least 3°C above the dew point. For optimum application properties bring the material to 21-27°C, unless specifically instructed otherwise, prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage in accordance with the information given in the STORAGE section of this data sheet.

Technical and application data herein is for the purpose of establishing a general guideline of the coating and proper coating application guidelines. Test performance results were obtained in a controlled laboratory environment and International Paint makes no claim that the exhibited published test results, or any other tests, accurately represent results actually found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance and use of the coating.

UNIT SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	20 lt	10 lt	20 lt	10 lt	10 lt

UNIT SHIPPING WEIGHT (TYPICAL)	Unit Size	Unit Weight
		20 lt

STORAGE	Shelf Life	Part A - 12 months at 25°C
		Part B - 6 months at 25°C

Subject to reinspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.

PLACE OF MANUFACTURE

Peoples Republic of China, Singapore, Malaysia, India. **Selection from this list as appropriate.**

IMPORTANT NOTE

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

© AkzoNobel, 2015

www.international-marine.com