

## IMO Resolution MSC.215 (82) compliant Zinc Silicate Shop Primer

**PRODUCT DESCRIPTION** A two pack, heat resistant, zinc silicate shop (pre-construction) primer providing good corrosion protection (even after heating up to 800°C), with minimum production of zinc salts. Suitable for high speed welding and cutting with excellent resistance to damage caused by welding, gas cutting and fairing thereby reducing secondary surface preparation requirements in comparison to typical zinc silicate products.

**INTENDED USES** As a shop (pre-construction) primer for the protection of steel during fabrication and assembly. Suitable for use with controlled cathodic protection. For use at Newbuilding.

**PRODUCT INFORMATION**

**Colour** NQA993-Grey (a range of colours are available in the USA only).  
**System Film Thickness** 1 coat at 15 microns dry (60 microns wet) per coat  
**Part B (Curing Agent)** NQA996 (NQA997 in USA only)

Note: NQA996 & NQA997 differ in solvent blend only and therefore the composition of the dry film is the same regardless of the binder used.

**Volume Solids** 25% ±2% (ISO 3233:1998)  
**Mix Ratio** 0.50 volume(s) Part A to 1 volume(s) Part B  
**Specific Gravity** Paste (Part A) 2.37-2.46  
 Binder (Part B) 0.945-0.975 (0.875-0.9 in UK)  
 Mixed Paint 1.42-1.47 (1.377-1.418 in UK)

**Theoretical Coverage** 16.67 m<sup>2</sup>/litre at 15 microns dft, allow appropriate loss factors  
**Method of Application** Airless Spray, Brush, Conventional Spray, Roller  
**Flash Point (Typical)** Part A 5°C; Part B 10°C; Mixed 14°C  
 (Product produced and supplied in North America has flash points of Part A 15°C, Part B 16°C and Mixed 15°C respectively due to locally sourced solvents. There is no detrimental effect on product performance.)

Drying Information	Substrate Temperature							
	5°C	10°C	25°C	35°C				
Hard Dry [ISO 9117-1:2009]			5 mins	4 mins				
Pot Life	24 hrs	24 hrs	24 hrs	8 hrs				
Overcoating Data - see limitations	Substrate Temperature							
	5°C		10°C		25°C		35°C	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max

**Note** Consult International Paint, minimum of 7 days for appropriate primers.

**REGULATORY DATA**

**VOC** 636 g/lt as supplied (EPA Method 24)  
 457 g/kg of liquid paint as supplied. EU Solvent Emissions Directive (Council Directive 1999/13/EC)

**Note:** VOC values are typical and are provided for guidance purposes only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

**EPA** VOC of USA supplied material 648 g/lt (5.41 lb/US Gal) as supplied (EPA Method 24)

## IMO Resolution MSC.215 (82) compliant Zinc Silicate Shop Primer

### CERTIFICATION

When used as part of an approved scheme, this material has the following certification:

- Weld Quality - Approval of Prefabrication Primers (LR)
- Fire Resistance - Marine Equipment Directive compliant
- IMO PSPC Resolution MSC.215 (82) - American Bureau of Shipping (ABS)
- IMO PSPC Resolution MSC.215 (82) - Bureau Veritas (BV)
- IMO PSPC Resolution MSC.215 (82) - DNV GL
- IMO PSPC Resolution MSC.215 (82) - Lloyds Register (LR)
- IMO PSPC Resolution MSC.215 (82) - Registro Italiano Navale (RINA)

Consult your International Paint representative for details.

Approvals issued by external bodies may be dependent upon formulation and/ or manufacturing site.

---

### SURFACE PREPARATIONS

Use in accordance with the standard Worldwide Marine Specifications.

All surfaces to be coated should be clean, dry and free from contamination.

### NEWBUILDING

Shop primers should be applied using automatic blasting/spraying equipment.

Blast to a minimum of Sa2½ (ISO 8501-1:2007). Steel grit or a mixture of steel grit of particle size 0.6-1.0mm and steel shot of particles size 0.6-1.4mm are normally used to give a predominantly angular profile.

Apply Interplate 997 before oxidation occurs. If oxidation does occur the entire oxidised area should be reblasted to the standard specified above.

Consult your International Paint representative for specific recommendations.

### Cleanliness

All surfaces to be coated must be clean, dry and free from contamination.

Residual dust levels prior to paint application must not exceed rating "1" for dust size classes "3", "4" or "5" (ISO 8502-3:1993).

Residual soluble salt levels prior to coating application must not exceed 50mg/m<sup>2</sup> as extracted and measured in accordance with ISO 8502-6 (1995) and ISO 8502-9 (1998) respectively.

### Surface profile

The surface profile must lie in the range 30-75 microns (ISO 8503-1/2:1988).

### NOTE

**For use in Marine situations in North America, the following surface preparation standards can be used:  
SSPC-SP10 in place of Sa2½ (ISO 8501-1:2007)**

## IMO Resolution MSC.215 (82) compliant Zinc Silicate Shop Primer

### APPLICATION

<b>Mixing</b>	Material is supplied in 2 containers as a unit. Always mix a complete unit in the proportions supplied. Agitate Paste (Part A) with a power agitator, slowly add binder (Part B) while agitating. Allow to mix for at least 5 minutes, sieve through a 30-60 mesh screen before use. Continue stirring during use.
<b>Thinner</b>	GTA820 (Winter Grade), GTA840 (Summer Grade) Not Recommended. Use International GTA820, GTA840 only in exceptional circumstances (max 5% by volume). DO NOT thin more than allowed by local environmental legislation.
<b>Airless Spray</b>	Recommended Tip Range 0.48-0.58 mm (19-23 thou) Total output fluid pressure at spray tip not less than 60 - 100 kg/cm <sup>2</sup> (850 - 1420 p.s.i.)
<b>Conventional Spray</b>	Use suitable proprietary equipment. Thinning may be required.
<b>Brush</b>	Application by brush is recommended for small areas only. Multiple coats may be required to achieve specified film thickness.
<b>Roller</b>	Application by roller is recommended for small areas only. Multiple coats may be required to achieve specified film thickness. Brush and roller are not suitable for application of full coats. Airless spray should be used for the latter.
<b>Cleaner</b>	International GTA820/GTA840
<b>Work Stoppages and Cleanup</b>	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA820/GTA840. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units. Clean all equipment immediately after use with International GTA820/GTA840. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays. Do not exceed pot life limitations. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.
<b>Welding</b>	<b>Hot Work</b> In the event welding or flame cutting or fairing is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety in Welding and Cutting."

### SAFETY

**All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.**

**Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.**

#### EMERGENCY CONTACT NUMBERS:

USA/Canada - Medical Advisory Number 1-800-854-6813

Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191

R.O.W. - Contact Regional Office

## IMO Resolution MSC.215 (82) compliant Zinc Silicate Shop Primer

### LIMITATIONS

Drying times will depend on the substrate temperature and ventilation conditions. If the relative humidity is below 50%, cure will be retarded. Interplate 997 is not recommended for manual spray application. Shop primers are not recommended for use as touch-up primers after fabrication.

### Film Thickness

#### Minimum film thickness

Film thicknesses below the specified 15 microns may result in premature breakdown of the shop primer and substrate corrosion, necessitating additional secondary surface preparation.

#### Maximum film thickness

Film thicknesses above the specified 15 microns may adversely affect welding and cutting properties and may affect the performance of subsequently applied coating systems. Thicknesses above 25 microns should be avoided.

Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Paint representative for specific recommendations. The temperature of the surface to be coated must be at least 3°C above the dew point. For optimum application properties bring the material to 21-27°C, unless specifically instructed otherwise, prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage in accordance with the information given in the STORAGE section of this data sheet. Technical and application data herein is for the purpose of establishing a general guideline of the coating and proper coating application guidelines. Test performance results were obtained in a controlled laboratory environment and International Paint makes no claim that the exhibited published test results, or any other tests, accurately represent results actually found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance and use of the coating.

UNIT SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	20 lt	6.67 lt	20 lt	13.33 lt	15 lt
	5 US gal	1.67 US gal	5 US gal	3.33 US gal	3.5 US gal

Part B is supplied in a polyethylene container  
For availability of other unit sizes consult International Paint

UNIT SHIPPING WEIGHT (TYPICAL)	Unit Size		Unit Weight
	20 lt		30.67 Kg
	5 US gal		64.6 lb

STORAGE	Shelf Life	Low flash storage required.
		Part A - 12 months at 25°C Part B - 6 months at 25°C

### PLACE OF MANUFACTURE

United Kingdom, USA. Selection from this list as appropriate.

### IMPORTANT NOTE

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.*

*This Technical Data Sheet is available on our website at [www.international-marine.com](http://www.international-marine.com) or [www.international-pc.com](http://www.international-pc.com), and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.*

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

© AkzoNobel, 2019

[www.international-marine.com](http://www.international-marine.com)