

ENA301/H INTERSHIELD 300 ALUMINIUM PART A

4

10/27/14

1.

1.1. INTERSHIELD 300 ALUMINIUM PART A
ENA301/H

1.2.

1.3.

626-6

(8-6)

1.4.

055-632-6286(),055 586 2310()

055 587 6276()

055 586 2310()

055 586 2310()

2.

2.1.

3; H226

/

2;H315

/

2;H319

1;H317

2;H411

2.2.

11 , 12



H315
H317
H319
H411

[]:

P210 / / /
P260 / /
P261 / /가 / / /
P262 , ,
P264
P272
P273
P280 / / /

[]:

P301+310 : /
P302+352 :
P303+361+353 () :
/
P305+351+338 가 : .가

P312 /
P321 ().
P331
P333+313 /
P337 :
P362
P363
P370 :
P378 , , ,
P391

[]:

P403+233 가

[]:

P501 ()

2.3.
PBT (,) vPvB (,)

3.

/	%	GHS	
Epoxy resin (av.mol.wt.<700) CAS No: 0025068-38-6	30-40	/ 2;H319 / 2;H315 1;H317 - 2;H411	[1]
xylene CAS No: 0001330-20-7	10-20	3; H226 - 4;H312 - 4;H332 / 2;H315 / 2AIH319 -1 ;H336	[1][2]

		- 1;H372	
Aluminium, alkyls CAS No: 0007429-90-5	5-10	Water react. 2;H261 H250	[1][2]
Solvent naphtha (petroleum), light aromatic CAS No: 0064742-95-6	5-10	1;H304	[1]
n-Butanol CAS No: 0000071-36-3	2.5-5	3; H226 - 4;H302 -1 ;H335 / 2;H315 / 1;H318 -1 ;H336	[1][2]
Ethylbenzene CAS No: 0000100-41-4	1-2.5	2;H225 - 4;H332 - 3;H373 1;H304 / 2;H315 / 2;H319 -1 ;H335	[1][2]
polyamide dispersion CAS No: 0055349-01-4	<1	1;H317 - 4;H413	[1]
Methanol CAS No: 0000067-56-1	<1	2;H225 - 3;H331 - 3;H311 - 3;H301 -1 1;H370	[1][2]
	20-30	---	---

- 1)
- 2) 가
- 3) PBT vPvB
16

4.

4.1.

가

가

4.2. 가 /

4.3.

5. ,

5.1.

; , , , .

Note; 가 .

가 .

5.2.

가 :

5.3.

가 .
가 .

6.

6.1.

가 가 가 , 가

6.2.

가 .

6.3.

.8 .

, , 가 . (13 .)

가 .

가 .

, 가 , 가 .

7.

7.1.

가 .

가 (LEL) (OEL)

가

가

가 (LEL) (OEL)

7.2. ()

, 8

가

가

61

가

1

7.3. Specific end use(s)

가

, 가

. 3

Hot surfaces, Sparks,

가

(60% ,)

8.

8.1.

(OEL)

(ACGIH)

(ACGIH)

ppm

mg/m³

ppm

mg/m³

Aluminium, alkyls

2

Ethylbenzene

125

545

100

435

Methanol

250

310

200

260

n-Butanol

C50

C150

Talc

2

xylene

150

655

100

434

(P) (Peak exposure limit)

(R)

(Sk)

(Sen)

(Cat 1)

(Cat 2)

(Cat 3)

가

DNEL/PNEC

8.2.

가

가

(visor)

(overall)

가

가

가

가

9.

pH

/ (°C)

(°C)

65

28

(= 1)

(,)

/

: 1.1 (xylene)

: 6.6 (xylene)

(Pa)

1.33

n-

/

(Log Kow)

9.2.

10.

10.1.

10.2.

.(Section 7)

가

10.3.

가

10.4.

.(7 .)

10.5.

10.6.

가

11.

(OEL)

가

가

Data

	LD50, mg/kg	LD50, mg/kg	LD50, mg/L/4hr	/ LD50, mg/L/4hr
Aluminium, alkyls - (7429-90-5)				
Epoxy resin (av.mol.wt.<700) - (25068-38-6)	2,000.00,	2,000.00,		
Ethylbenzene - (100-41-4)	3,500.00,	15,433.00,	17.20,	
Methanol - (67-56-1)	5,628.00,	15,800.00,	85.00,	
n-Butanol - (71-36-3)	2,292.00,	3,430.00,		
polyamide dispersion - (55349-01-4)				
Solvent naphtha (petroleum), light aromatic - (64742-95-6)	6,800.00,	3,400.00,		
xylene - (1330-20-7)	4,299.00,	1,548.00,		20.00,

()		
()		
()		
/	2	
/	2	
	1	
(1)		
()		

12.

12.1.

Dangerous Preparations Directive 1999/45/EC

가
(3)

가

	96 hr LC50 mg/l	49 hr EC50 mg/l	ErC50 mg/l
Epoxy resin (av.mol.wt.<700) - (25068-38-6)	3.10, Pimephales promelas	1.40, Daphnia magna	

xylene - (1330-20-7)	3.30, Oncorhynchus mykiss	8.50, Palaemonetes pugio	100.00 (72 hr), Chlorococcales
Aluminium, alkyls - (7429-90-5)	0.12, Oncorhynchus mykiss	3.50, Daphnia magna	
Solvent naphtha (petroleum), light aromatic - (64742-95-6)	9.22, Oncorhynchus mykiss	6.14, Daphnia magna	19.00 (72 hr), Selenastrum capricornutum
n-Butanol - (71-36-3)	1,376.00, Pimephales promelas	1,328.00, Daphnia magna	500.00 (96 hr), Scenedesmus subspicatus
Ethylbenzene - (100-41-4)	4.20, Oncorhynchus mykiss	2.93, Daphnia magna	3.60 (96 hr), Pseudokirchneriella subcapitata
polyamide dispersion - (55349-01-4)			
Methanol - (67-56-1)	100.00, Pimephales promelas	10,000.00, Daphnia magna	16.912 (96 hr), Ulva pertusa

12.2.

가 .

12.3.

12.4.

12.5. , , 가
PBT (,) vPvB (,) .

12.6.

13.

13.1.

가

14.

14.1. 1263

14.2.

14.3.

1263, , 3, III, 3[Y]

IMDG Class/Div. 3

EmS F-E,S-E

ICAO/IATA 3

14.4. III

14.5.

:

IMDG : (Epoxy Resin)

14.6. 가 가

14.7. MARPOL73/78 Annex II IBC Code .

15.

4 , 2 , III

MSDS 8 .

Aluminium, alkyls (0007429-90-5)
n-Butanol (0000071-36-3)
Ethylbenzene (0000100-41-4)
Talc (0014807-96-6)

(CMR):

Silica(quartz) (0014808-60-7)
ethanol (0000064-17-5)
Ethylbenzene (0000100-41-4)

:

Aluminium, alkyls (0007429-90-5)
n-Butanol (0000071-36-3)
Ethylbenzene (0000100-41-4)
xylene (0001330-20-7)

:

Aluminium, alkyls (0007429-90-5)
n-Butanol (0000071-36-3)
Ethylbenzene (0000100-41-4)
xylene (0001330-20-7)

가 :

()

:

()

:

()

:

()

Epoxy resin (av.mol.wt.<700) (0025068-38-6)

Group I:

()

Group II:

Aluminium, alkyls (0007429-90-5)
Epoxy resin (av.mol.wt.<700) (0025068-38-6)
Ethylbenzene (0000100-41-4)
xylene (0001330-20-7)

⋮
()

()

⋮

Talc (0014807-96-6)

16.

: 10/27/2014

: 4

: 08/14/2007

MSDS KOSHA, NITE, ESIS, NLM, SIDS, IPCS, NCIS

SDS

Section 3 Phrases

- H225
- H226
- H250
- H261
- H302
- H304
- H312
- H315
- H317
- H318
- H319
- H332
- H335
- H336
- H372
- H373
- H411

가

This SDS is valid for 5 years from the revised date on page 1.



