

Water-Based Acrylic Finish

PRODUCT DESCRIPTION A water based, low odour acrylic finish with good gloss, gloss retention, easy clean and non - yellowing properties.

INTENDED USES For use on internal accommodation areas, store rooms etc. Intercryl 507 is part of a specified, approved, fire retardant scheme.
For use at Newbuilding or Maintenance & Repair.

PRODUCT INFORMATION

Colour	WXB000-White, WXE000-Dawn Grey
Finish/Sheen	High Gloss
Part B (Curing Agent)	Not applicable
Volume Solids	40% ±2% (ISO 3233:1998)
Mix Ratio	Not applicable
Typical Film Thickness	50 microns dry (125 microns wet). Range 30 - 60 microns dry (75 - 150 microns wet) may be specified depending upon end use and method of application.
Theoretical Coverage	8.00 m ² /litre at 50 microns dft, allow appropriate loss factors
Method of Application	Airless Spray, Brush, Conventional Spray, Roller

Drying Information	5°C	10°C	25°C	35°C
Touch Dry [ISO 9117/3:2010]	120 mins	100 mins	60 mins	30 mins
Hard Dry [ISO 9117-1:2009]	16 hrs	12 hrs	4 hrs	4 hrs

Overcoating Data - see limitations	Substrate Temperature							
	5°C		10°C		25°C		35°C	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Intercryl 507	16 hrs	ext	14 hrs	ext	8 hrs	ext	4 hrs	ext

REGULATORY DATA

VOC	135 g/lit as supplied (EPA Method 24) 113 g/kg of liquid paint as supplied. EU Solvent Emissions Directive (Council Directive 1999/13/EC)
------------	--

Note: VOC values are typical and are provided for guidance purposes only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

Water-Based Acrylic Finish

CERTIFICATION

When used as part of an approved scheme, this material has the following certification:

- Fire Resistance - Surface Spread of Flame (WFR) - (BS476:Part 7)

Consult your International Paint representative for details.

SYSTEMS AND COMPATIBILITY

Consult your International Paint representative for the system best suited for the surfaces to be protected.

SURFACE PREPARATIONS

Use in accordance with the standard Worldwide Marine Specifications.

All surfaces to be coated should be clean, dry and free from contamination.

High pressure fresh water wash or fresh water wash, as appropriate, and remove all oil or grease, soluble contaminants and other foreign matter in accordance with SSPC-SP1 solvent cleaning.

NEWBUILDING

Intercryl 507 should be applied over Intercryl 506, the surface of which should be dry and free of all contaminants.

Intercryl 507 must be applied within the overcoating intervals specified on the Intercryl 506 data sheet.

MAJOR REFURBISHMENT

Intercryl 507 should be applied over Intercryl 506, the surface of which should be dry and free of all contaminants.

Intercryl 507 must be applied within the overcoating intervals specified on the Intercryl 506 data sheet.

REPAIR

Repair corroded/damaged areas with recommended anticorrosive primer. Apply Intercryl 507 within the overcoating intervals specified (consult primer data sheet).

Consult your International Paint representative for specific recommendations.

Water-Based Acrylic Finish

APPLICATION

Mixing	This material is a one pack coating and should always be mixed thoroughly with a power agitator before application.
Thinner	Not recommended. Use water only in exceptional circumstances (max 5% by volume).
Airless Spray	Recommended Tip Range 0.33-0.43 mm (13-17 thou) Total output fluid pressure at spray tip not less than 211 kg/cm ² (3000 p.s.i.)
Conventional Spray	Suitable. Use suitable proprietary equipment. Thinning may be required.
Brush	Suitable.
Roller	Suitable.
Cleaner	Water/Detergent
Work Stoppages and Cleanup	Thoroughly flush all equipment with Water/Detergent. All unused material should be stored in tightly closed containers. Partially filled containers may show surface skinning and/or viscosity increase of the material after storage. Material should be filtered prior to use.
Welding	In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety in Welding and Cutting."

SAFETY

All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.

Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.

EMERGENCY CONTACT NUMBERS:

USA/Canada - Medical Advisory Number 1-800-854-6813

Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191

R.O.W. - Contact Regional Office

Water-Based Acrylic Finish

LIMITATIONS

This product should not be exposed to temperatures of 0°C or below (protect from frost).

Do not apply at temperatures below 5°C.

Rate of drying is humidity and airflow dependant , Consult International Paint. Do not apply when relative humidity exceeds 85%.

Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Paint representative for specific recommendations. Apply in good weather. Temperature of the surface to be coated must be at least 3°C above the dew point. For optimum application properties bring the material to 21-27°C, unless specifically instructed otherwise, prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage in accordance with information given in the STORAGE Section of this data sheet. Technical and application data herein is for the purpose of establishing a general guideline of the coating application procedures. Test performance results were obtained in a controlled laboratory environment and International Paint makes no claim that the exhibited published test results, or any other tests, accurately represent results found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance and use of the coating.

In the overcoating data section 'ext' = extended overcoating period. Please refer to our Marine Painting Guide - Definitions and Abbreviations available on our website.

UNIT SIZE

Unit Size	Part A	
	Vol	Pack
20 lt	20 lt	20 lt
5 lt	5 lt	5 lt

For availability of other unit sizes consult International Paint

UNIT SHIPPING WEIGHT (TYPICAL)

Unit Size	Unit Weight
20 lt	25.9 Kg
5 lt	6.51 Kg

STORAGE

Shelf Life	12 months minimum at 25°C. Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.
------------	---

WORLDWIDE AVAILABILITY Consult International Paint.

IMPORTANT NOTE

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

© AkzoNobel, 2016

www.international-marine.com