

Inorganic Zinc Tank Coating

PRODUCT DESCRIPTION A two pack, FDA compliant zinc ethyl silicate tank coating.

INTENDED USES A tank coating suitable for the carriage of petroleum products, solvents (including methanol) and other neutral cargoes.
For use at Newbuilding or Maintenance & Repair.

PRODUCT INFORMATION

Colour	QHA126-Grey
Finish/Sheen	Not applicable
Part B (Curing Agent)	QHA125
Volume Solids	52% ±2% (ISO 3233:1998)
Mix Ratio	2.83 volume(s) Part A to 1 volume(s) Part B
Typical Film Thickness	100 microns dry (192 microns wet)
Theoretical Coverage	5.20 m ² /litre at 100 microns dft, allow appropriate loss factors
Method of Application	Airless Spray, Brush, Conventional Spray, Roller
Flash Point (Typical)	Part A 32°C; Part B 15°C; Mixed 21°C
Induction Period	Not required

Drying Information	5°C	10°C	25°C	35°C
Touch Dry [ISO 9117/3:2010]	60 mins	60 mins	60 mins	30 mins
Hard Dry [ISO 9117-1:2009]	4 hrs	3 hrs	2 hrs	2 hrs
Pot Life	8 hrs	7 hrs	4 hrs	2 hrs

Overcoating Data - see limitations	Substrate Temperature							
	5°C		10°C		25°C		35°C	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Interline 104	24 hrs	10 days	24 hrs	10 days	24 hrs	10 days	24 hrs	8 days

REGULATORY DATA **VOC** 618 g/lit as supplied (EPA Method 24)
258 g/kg of liquid paint as supplied. EU Solvent Emissions Directive (Council Directive 1999/13/EC)

Note: VOC values are typical and are provided for guidance purposes only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

Inorganic Zinc Tank Coating

SYSTEMS AND COMPATIBILITY

Consult your International Paint representative for the system best suited for the surfaces to be protected. When using in cargo tanks, consult the Interline 104 Cargo Tank Application Guidelines.

SURFACE PREPARATIONS

Use in accordance with the standard Worldwide Marine Specifications.

All surfaces to be coated should be clean, dry and free from contamination.

High pressure fresh water wash or fresh water wash, as appropriate, and remove all oil or grease, soluble contaminants and other foreign matter in accordance with SSPC-SP1 solvent cleaning.

NEWBUILDING

Where necessary, remove weld spatter and smooth weld seams and sharp edges.

This product must only be applied to surfaces prepared by abrasive blast cleaning to Sa2½ (ISO 8501-1:2007).

A sharp, angular surface profile of 30-75 microns is recommended.

MAJOR REFURBISHMENT

Abrasive blast clean to Sa2½ (ISO 8501-1:2007).

Interline 104 must be applied before oxidation of the steel occurs. If oxidation does occur the entire oxidised area should be reblasted to the standard specified above.

Surface defects revealed by the blast cleaning process, should be ground, welded, or treated in the appropriate manner.

A sharp, angular surface profile of 30-75 microns is recommended.

REPAIR

Consult International Paint.

Consult your International Paint representative for specific recommendations.

NOTE

For use in Marine situations in North America, the following surface preparation standards can be used: SSPC-SP10 in place of Sa2½ (ISO 8501-1:2007)

Inorganic Zinc Tank Coating

APPLICATION

Mixing	Interline 104 is supplied in 2 parts, a paste component (Part A) and a liquid binder component (Part B). The binder (Part B) should be slowly added to the paste (Part A) whilst stirring with a mechanical agitator. DO NOT ADD PASTE TO LIQUID. Material should be sieved prior to application and should be constantly agitated in the pot during spraying. Once the unit has been mixed it should be used within the working pot life. This is a low viscosity material and agitation is required during application to ensure homogeneity is maintained.
Thinner	Recommended only for conventional spray application.
Airless Spray	Recommended Tip Range 0.46-0.61 mm (18-24 thou) Total output fluid pressure at spray tip not less than 112 - 141 kg/cm ² (1590 - 2010 p.s.i.)
Conventional Spray	Use suitable proprietary equipment. Thinning may be required.
Brush	Application by brush is recommended for small areas only. Multiple coats may be required to achieve specified film thickness.
Roller	Application by roller is recommended for small areas only. Multiple coats may be required to achieve specified film thickness.
Cleaner	International GTA803
Work Stoppages and Cleanup	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA803. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units. Clean all equipment immediately after use with International GTA803. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature, relative humidity and elapsed time, including any delays. Do not exceed pot life limitations. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.
Welding	In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety in Welding and Cutting."

SAFETY

All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.

Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.

EMERGENCY CONTACT NUMBERS:

USA/Canada - Medical Advisory Number 1-800-854-6813

Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191

China – Contact (86) 532 83889090

R.O.W. - Contact Regional Office

Inorganic Zinc Tank Coating

LIMITATIONS

International Paint should be consulted to confirm that the tank coating is suitable for the range of cargoes to be carried.

The drying times and overcoating intervals may alter due to various on-site factors such as humidity, tank configuration, ventilation rates, etc.

Consult the detailed coating application procedures for the time interval required between coating completion and cargo loading.

Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Paint representative for specific recommendations.

Apply in good weather. Temperature of the surface to be coated must be at least 3°C above the dew point. For optimum application properties bring the material to 21-27°C, unless specifically instructed otherwise, prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage in accordance with information given in the STORAGE Section of this data sheet. Technical and application data herein is for the purpose of establishing a general guideline of the coating application procedures. Test performance results were obtained in a controlled laboratory environment and International Paint makes no claim that the exhibited published test results, or any other tests, accurately represent results found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance and use of the coating.

UNIT SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	10 lt	7.39 lt	10 lt	2.61 lt	5 lt

For availability of other unit sizes consult International Paint

UNIT SHIPPING WEIGHT (TYPICAL)	Unit Size	Unit Weight
	10 lt	25.11 Kg

STORAGE	Shelf Life	Part A - 12 months minimum from date of manufacture when maintained in protected storage at temperatures up to 25°C. Part B - 4 months minimum from date of manufacture when maintained in protected storage at 25°C. Subject to reinspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.

WORLDWIDE AVAILABILITY Consult International Paint.

IMPORTANT NOTE

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

© AkzoNobel, 2018

www.international-marine.com